

Contact lenses as drug controlled release systems: a narrative review

As lentes de contacto como sistema de libertação controlada de fármacos: uma revisão narrativa

Helena Prior Filipe^{1,4}, José Henriques², Pedro Reis^{3,4}, Pedro Cruz Silva⁴, Maria João Quadrado⁵, Ana Paula Serro⁶

ABSTRACT

Topically applied therapy is the most common way to treat ocular diseases, however given the anatomical and physiological constraints of the eye, frequent dosing is required with possible repercussions in terms of patient compliance. Beyond refractive error correction, contact lenses (CLs) have, in the last few decades emerged as a potential ophthalmic drug controlled release system (DCRS). Extensive research is underway to understand how to best modify CLs to increase residence time and bioavailability of drugs within therapeutic levels on the ocular surface. These devices may simultaneously correct ametropia and have a role in managing ophthalmic disorders that can hinder CL wear such as dry eye, glaucoma, ocular allergy and cornea infection and injury. In this narrative review the authors explain how the ocular surface structures determine drug diffusion in the eye and summarize the strategies to enhance drug residence time and bioavailability. They synthesize findings and clinical applications of drug soaked CLs as DCRS combined with delivery diffusion barriers, incorporation of functional monomers, ion related controlled release, molecular imprinting, nanoparticles and layering. The authors draw conclusions about the impact of these novel ophthalmic agents delivery systems in improving drug transport in the target tissue and patient compliance, in reducing systemic absorption and undesired side effects, and discuss future perspectives.

Keywords: Contact lenses; Dry eye syndrome; Glaucoma; Allergy; Keratitis; Bioavailability; Residence time; Molecular imprinting; Nanoparticles

RESUMO

A forma mais frequente de aplicação terapêutica em oftalmologia consiste na instilação de gotas oculares, mas dadas as limitações anatómicas e fisiológicas do olho, é necessária dosagem frequente com possível repercussão na adesão do paciente à terapêutica. Nas últimas décadas, as lentes de contacto (CLs) têm surgido como um potencial sistema de libertação controlada de fármacos na superfície ocular (DCRS) para correção do erro refrativo. Está em curso uma extensa investigação para entender a melhor forma de modificar as CLs, de modo a aumentar o tempo de residência e a biodisponibilidade do medicamento na superfície ocular dentro de níveis terapêuticos. Ao corrigirem a ametropia, estes dispositivos poderão simultaneamente desempenhar um papel na gestão de perturbações oftalmológicas, tais como a síndrome do olho seco, glaucoma, alergia ocular e infecção corneana, que podem comprometer o porte seguro e confortável das CLs. Nesta revisão narrativa, os autores explicam como as estruturas da superfície ocular determinam a difusão de fármacos no olho e sintetizam as estratégias para aumentar a permanência e biodisponibilidade dos mesmos. Em seguida, apresentam os resultados e as aplicações clínicas das CLs embebidas em fármacos, como DCRS, através da incorporação de barreiras de difusão, de monómeros funcionais, da libertação controlada por iões, da impressão molecular, de nanopartículas e pelo processo camada sobre camada. Os autores concluem avaliando o impacto destes novos sistemas de entrega de agentes farmacológicos ao melhorar o seu transporte no tecido alvo, reduzindo a sua absorção sistémica e os seus efeitos colaterais indesejáveis, e discutem perspectivas futuras.

Descritores: Lentes de contacto; Síndrome de olho seco; Glaucoma; Alergia; Queratite; Biodisponibilidade; Tempo de permanência; Impressão molecular; Nanopartículas

¹ Department of Ophthalmology, Hospital of the Armed Forces - Lisbon, Azinhaga dos Ulmeiros, Paço do Lumiar, Lisbon, Portugal

² Department of Retina and Vitreo, Institute of Ophthalmology Dr. Gama Pinto, Lisbon, Portugal; IRL – Institute of Retina of Lisbon, Lisbon, Portugal.

³ Department of Ophthalmology, Hospital of the Armed Forces, Lisbon, Portugal; Department of Ophthalmology, Hospital of SAMS, Lisbon, Portugal.

⁴ Department of Ophthalmology, Hospital of SAMS, Lisbon, Portugal.

⁵ Department of Ophthalmology, Hospitals of the University of Coimbra, Faculty of Medicine of the University of Coimbra, Coimbra, Portugal.

⁶ Center of Structural Chemistry, Complex I, Instituto Superior Técnico, University of Lisbon, Lisbon, Portugal; Center of Interdisciplinary Investigation Egas Moniz, Instituto Superior de Ciências da Saúde Egas Moniz, Caparica, Portugal.

The authors declare no conflicts of interests.

Received for publication 13/03/2016 - Accepted for publication 05/04/2016

INTRODUCTION

Poly (methyl methacrylate) (PMMA) was the first successful polymeric contact lens (CL) material introduced in the market in the 1960s. These CLs are rigid, time consuming to fit and not very comfortable to wear. Research into new types of polymers led to the development of hydrogels, the first biomaterials designed for clinical use. They consist of a cross-linked polymeric network with a high capacity of water absorption and have been extensively used in numerous biomedical applications since the early 1960s. In 1965 Wichterle et al. pioneered the suggestion of their potential use in ophthalmic drug delivery as bandage soft CLs (SCL). Although the new materials were quite hydrophilic, which kept the lens soft and flexible, their gas-permeability was still low. The introduction of highly permeable silicone hydrogel (SH) in the late 1990s overcame SCLs' insufficient oxygen transmission to the cornea. SHCLs represented a significant leap for further research on CLs as ophthalmic drug controlled release systems (DCRS).¹⁻⁴

Several factors emphasize their singular importance in the field of ocular therapeutics: the approximately 125 million worldwide CL wearers; well-studied CL biocompatibility and transparency; the familiarity of their use with minimal effect on ocular functions and a large residence time in the eye. Eye physiological and anatomical constraints compromise the correct drug concentration and optimal absorption of pharmacological agents at the specific action site requiring multiple dosage of eye drops eventually associated with noncompliance, overdosing and unwanted systemic side effects. The latter are especially important in chronic ocular diseases such as glaucoma, allergy and dry eye as in those requiring a timely and effective control, as infectious keratitis and corneal wound healing.⁵⁻⁸

Drug Routes, Ocular Surface and Effectiveness Constraints

The three main routes of administration of ocular medication are systemic, intraocular and topical. Effective systemic delivery requires a high drug concentration to achieve a therapeutically effective dose within the eye. Intraocular drug administration is effective but as with any invasive procedure it carries a not insignificant risk, especially if repeated treatments are required. Topically applied medication represents approximately 90% of aqueous ophthalmic formulations. They are simple to formulate, have minimal storage limitations and can be self-administered. However, significant drug losses occur with this administration form, which limit its therapeutic efficiency. Understanding the structure of the ocular surface, tear drainage physiology and drug diffusion mechanisms can shed an understanding on ocular drug pharmacokinetic and the reasons for such inefficiency.^{9,10}

If the human tear film is approximately 7 μ l, a 30 μ l eye drop is rapidly squeezed out of the eye, the remainder being mixed in the tear volume with an estimated residence time of approximately 2 - 3 minutes. The conjunctiva presents a higher permeability than the cornea due to its vascularized nature and an area that is approximately 16 - 18 times larger. Thus, most of the solutes are absorbed by the conjunctiva, drained by the lacrimal system into the nose and enter the systemic circulation with potential unwanted systemic side effects. In this context, only 1-7% of the medication within an eye drop reaches the target tissue with effective therapeutic effect thus justifying multiple dosing over extended periods with potential association with low compliance or drug overdosing.^{3, 10, 11}

The precorneal tear film allows corneal hydration and provides an epithelium-tear interface able to create a high refractive index. It presents an inner mucous layer anchored by microvilli to the epithelium, a middle aqueous layer with mucin and free lipid and an external thin lipid layer. It is divided into three compartments: precorneal, conjunctiva and tear menisci and is bounded by the corneal and the conjunctiva epithelia. CLs divide the tear film into a pre-lens tear film (PLTF) and a 4 micra thick post-lens tear film or pre-ocular tear film (POLTF), through which CL drug diffusion occurs. Eye opening leads to a limited drug release towards the PLTF and the CL motion promotes drug diffusion from the POLTF into the cornea or radially outwards from the CL into the tear lake.¹⁰

The cornea is a multilayer structure with epithelium, stroma, and endothelium separated by the Bowman and Descemet's membranes. The cornea has both lipophilic and hydrophilic properties, which explains a transport resistance to hydrophilic drugs of approximately 90% and about 10% to hydrophobic preparations. Corneal diffusion is the main route for topically applied drug absorption leaving a lesser role for the conjunctival/scleral route to play in. Corneal epithelium is a stratified layer presenting Ca²⁺-dependent membrane adherent regions (zonula occludens, zonula adherens and desmosomes) creating tight junctions, highly resistant to drug diffusion. Bowman's membrane is a transitional and acellular structure approximately 8-14 μ m thick. Corneal stroma is a gel-like layer with 80% of water, collagen, mucopolysaccharides and proteins, and represents approximately 90% of the total thickness (around 500 μ m) of the cornea. Due to solubility and partition coefficient limitation it shows significant diffusion resistance for lipophilic drugs and minimal for hydrophilic drugs. Descemet's membrane is an approximately 6 μ m thick membrane deposited by the endothelial cells. These loose epithelia-like cells regulate stromal hydration and maintain the cornea transparent. They form a monolayer of cells of about 13 μ m of thickness, the endothelium that provides little resistance to paracellular drug transportation.^{10, 12, 13}

The conjunctiva comprises several layers of epithelial and goblet cells that line the palpebral, culs de sac and the bulbar ocular surface to the corneal limbus. Most of the apical epithelial cells express mucin on their surface to create a protective glycocalyx. Goblet cells secrete gel-forming mucins that are relevant for eye lubrication and protection. The lacrimal gland produces smaller mucins. Diffusion through conjunctival epithelial cells follows a para-cellular path, ion channels, water channels, co-transporters, and transport pumps for ion, glucose, and water located in the cell membrane.^{10, 13}

Drainage of the tear film from the eye is an active process that depends on blinking.^{3, 10}

New delivery systems and devices to improve drug bioavailability

Morrison and Khutoryanskiy categorize the strategies to promote drug residence time and diffusion into the eye into three groups: Drug Solubility and Penetration Enhancement, Ocular Implants and Drug Retention from which we will emphasize CLs¹⁴ (Table 1).

Hydrotropic compounds improve aqueous **drug solubility** of poorly water-soluble compounds. Hydrotropes, such as caffeine, urea and nicotinamide enhance the solubility of riboflavin, while cyclodextrins form drug complexes with steroids, carbonyl anhydride inhibitors, pilocarpine and cyclosporine A (CyA), which are too large to partition to the cornea. Formulating for higher drug concentration also increases bioavailability. The

Table 1

Strategies to promote drug bioavailability.
Adapted from Morrison and Khutoryanskiy¹⁴

STRATEGIES TO PROMOTE DRUG BIOAVAILABILITY

Solubility and Penetration Enhancement

Hydrotropic compounds and higher drug concentration formulations.

Penetration enhancer formulations.

Ocular Implants

Implantable devices able to reside within the eye.

Retention Strategies

Viscosity-enhancing polymers, *in situ* gels and bio-adhesive formulations.

Ocular inserts to place and retain the agent in immediate contact with target tissue.

incorporation of compounds able to modify the corneal epithelia improves **drug penetration** and tissue drug partitioning. Benzalconium chloride (BAC), commonly used as a preservative in ocular drug formulations, cetylpyridinium chloride (CPC), ethylenediaminetetraacetic acid (EDTA), polyoxyethylene stearyl ether (PSE) and polyethoxylated castor oil (PCO) are examples of such compounds with well-known ocular surface toxic effects.^{15,16}

Intraocular lenses such as **ocular implants** can be modified to provide a controlled release of pharmacological agents and prevent intraocular inflammation, infection and lens posterior capsule opacification. There are already available in the market injectable intraocular implants to treat several chronic eye diseases ensuring a drug sustained release for 2.5-3 years: IluvienTM (Alimera Sciences Inc.) for diabetic macular edema, Retisert[®] (Bausch & Lomb) and Ozurdex[®] (Allergan) for chronic non-infectious posterior uveitis and DurasertTM (Pfizer Inc.) for glaucoma.^{14, 17-18}

Several **drug retention strategies** have been pursued to minimize the need for repeated treatments, especially in chronic diseases. They comprise **viscosity-enhancing polymers**, "**in situ**" **gels** undergoing phase transition from liquid to gel under physiological conditions, **mucoadhesives** and mucus-covered mucosal epithelial membranes, and **nanoparticles** drug-delivery systems as submicron structures in which drugs can be attached or encapsulated. Submicron-sized liposomes (ssLips) formulated as eye drops were effective in delivering coumarin-6 to the retina. **Ocular inserts** are drug-loaded devices designed to deliver a sustained drug release in direct contact with the conjunctiva or with the cornea and finally dissolve, erode or biodegrade. Ocusert[®] (Alza Corporation, Palo Alto) could deliver pilocarpine at either 20 $\mu\text{g}/\text{h}$ or 40 $\mu\text{g}/\text{h}$. Ocufit SR[®] (Escalon[®] Medical Corp) is a silicone elastomer rod-shaped device to be placed in the lower conjunctival fornix. Minidisc Ocular Therapeutic System (OTS, Bausch & Lomb, UK) is a drug-loaded polymer disc (4–5 mm) to be placed on the upper or lower fornix and deliver gentamicin or sulfisoxazole over a period of 3 to 14 days. The human amniotic membrane can be used as a drug-loaded ocular device to deliver ofloxacin for up to 7 hours *in vitro*. CLs are hard or soft ocular insert devices designed to fit directly onto the cornea, up to now, mainly to correct ametropia. SCLs are produced from hydrophilic or hydrophobic hydrogel polymers.

They can soak a large volume of aqueous solution relative to their anhydrous form with sufficient pharmaceutically active content able to diffuse from the polymer matrix into the tear film, bathe the eye and interact with the ocular tissue. Antibiotic and anti-inflammatory medication can be combined with a bandage CL to effectively manage ocular trauma, post-surgery conditions and promote epithelization. Several commercially available CLs were FDA approved to serve this purpose: Pure Vision (balafilcon A, Bausch+Lomb), Acuvue 2 (etafilcon A, Vistakon Inc.), Acuvue Oasys (senofilcon A, Vistakon Inc.), and Air Optix Night & Day (lotrafilcon A, Alcon).^{13-15, 19}

Generating Contact Lens based Drug Controlled Release Systems and Clinical Applications

The three main objectives underlying the development of DCRS based on CLs to enhance effective drug delivery are:

1. To improve and extend CL wear tolerance by incorporating anti dry eye and allergy agents' formulations.
2. To enhance patient compliance and reduce unwanted systemic side effects especially in chronic diseases such as glaucoma and dry eye whilst correcting ametropia.
3. To manage corneal wound healing such as "bandage lenses" by incorporating antimicrobial or anti-inflammatory agents.¹³

Offering a higher drug bioavailability to the cornea than conventional forms of treatment, CLs look the ideal carrier for ocular medication. Several strategies have been attempted to extend drug residence time and improve bioavailability including: soaking, incorporation of diffusion barriers, functional monomers, ligands, colloidal nanoparticles, molecular imprinting, and surface multi layering.¹⁵ (Figure 1).




Figure 1: Schematic diagram of strategies commonly used to improve drug release behavior from drug loaded CLs: 1- Soaking, 2- Incorporation of diffusion barriers such as vitamin E, 3- Incorporation of ligands/functional monomers in the polymeric matrix, 4- Molecular imprinting 5- Incorporation of drug-loaded nanoparticles or other colloidal nanostructured systems and 6- Surface coating by multi-layering colloidal nanoparticles and ligands.

CLs **drug soaking** is the earliest and simplest procedure to prepare drug lens combinations. The hydrophilic matrix of SCLs, ranging from 30 to 80 percent water, can absorb the drug from a soaking solution till equilibrium and then release it by simple diffusion when inserted in the eye. Intraocular pressure decreased from 55.6 to 30.0 mm Hg after two hours' use of a 1% pilocarpine loaded CL following this process, to treat acute angle closure glaucoma. Assays with SCL hydrogels of poly (2-hydroxyethyl methacrylate) (pHEMA) loaded in drug solutions containing, pilocarpine, levofloxacin, chlorhexidine, timolol and dexamethasone have demonstrated dynamic drug diffusion. More recently epidermal growth factor-soaked CLs have shown a positive therapeutic effect in a rabbit model wound healing and improved the healing time in non-significantly inflamed

corneas of patients with delayed corneal re-epithelization when compared to saline-soaked CLs.²¹⁻²⁸

SCL drug absorption and release is drug specific. Drug uptake depends on factors such as CL thickness and water content, the drug's molecular weight and gel matrix solubility. Similar CLs could absorb 7 to 8 mg of cromolyn sodium whereas only 0.07 mg of dexamethasone sodium phosphate. For most tested compounds such as prednisolone, pilocarpine, and ciprofloxacin, release by hydrophilic CLs was complete within 1 to 3 h, whereas ketotifen fumarate eluted from SHCLs over approximately 4-5 hours.^{8,29}

In vitro release studies are commonly carried out in conditions that are far from simulating the physiological delivery conditions. In order to more reliably predict the drug's release kinetics in the eye, it is crucial to develop microfluidic models that mimic, as closely as possible, the hydrodynamic conditions of the eye such as volume of liquid in contact with the ocular surface and tear flow rate.³⁰

Although simple, the drug loading method by soaking is limited by the rapid drug release and will be more appropriate to produce daily disposable therapeutic CLs. Research is now focused on novel approaches to control drug release. Several processes have been attempted to create additional barriers to CL drug release and generate ocular surface drug delivery over time at the correct dosage.³¹

Vitamin E aggregates incorporated within SHCLs block UV radiation and create a hydrophobic diffusion barrier to rapid drug diffusion without compromising proper oxygen permeability, ion permeability, and light refractive properties. Vitamin E loading proved to be very effective in increasing release duration of lidocaine, CyA, timolol, levofloxacin, chlorhexidine, dorzolamine, dexpantenol, betaine, dexamethasone and betamethasone, from hours to several days.³²⁻³⁷

Research on dry eye management has been increasingly focusing on the inflammatory aspect and CyA was FDA approved to treat moderate-to-severe dry eye disease. SHCLs were able to keep CyA delivery rates within therapeutic levels for 14 days. Vitamin E loaded CLs provided a CyA extended release up to one month. *In vivo* transport and toxicity studies are needed to assure the benefits of extended wear CLs for this purpose. CLs loaded with 30% of vitamin E showed a dexamethasone release time extended to 7-9 days for ACUVUE® OASYS™, NIGHT&DAY™ and O(2)OPTIX™, which is a 9 to 16 fold increase compared to drug release duration by CLs without vitamin E loading.^{11, 38, 39}

Serro et al. also showed that vitamin E loaded commercial CLs presented a significant increase of chlorhexidine and levofloxacin release duration while retaining critical properties for *in vivo* use.³⁵

Weak interactions between drugs and **polymer ligands** include hydrogen bonds, electrostatic interactions and host-guest interactions. They can induce drug loading and controlled release by ions in solution. Based on ion-exchange reaction these ligands store anionic or cationic drugs depending on the charge of their functional groups. Hydrogels containing cationic functional groups suit the delivery of anionic drugs whereas those containing anionic functional groups the release of cationic drugs. However, sustained release of these ions ligand-containing hydrogels last only several hours, making them unsuitable for extended drug delivery. Cyclodextrins (CDs) have hydrophobic internal cavities that can include "guest" drug molecules. Poly(2-hydroxyethyl methacrylate) hydrogels containing α -cyclodextrin (pHEMA/ α -

CD) have been investigated as a platform for sustained release of ophthalmic drugs. Incorporation of hyaluronic acid into hydrogels allowed timolol and ciprofloxacin release for a prolonged period.³⁹⁻⁴²

The incorporation of **functional monomers** able to interact with the drug in the hydrogels may prolong release duration. Increased interaction of the drug with these monomers delays its diffusion from the hydrogel. For example, the combination of the hydrophobic monomer 3-(trimethoxy-silyl) propyl methacrylate and the ionic monomer N,N-dimethylaminoethyl methacrylate improved insulin and protamine loading and allowed their extended release from pHEMA SCLs. Andrade-Vivero et al. reported that the incorporation of 4-vinyl-pyridine (VP) and N-(3-aminopropyl) methacrylamide (APMA) monomers increased the amount of loaded ibuprofen up to 10-fold and diclofenac up to 20-fold without compromising lens properties. The sustained drug release process from pHEMA-VP lasted for at least 24 hours for ibuprofen and almost 1 week for diclofenac. Kim et al. designed a SH comprising a hydrophilic monomer N,N-dimethylacrylamide (DMA) and a silicone monomer methacryloxypropyltris(trimethylsiloxy)silane (TRIS), with a new macromer bis- α , ω -methacryloxypropyl polydimethylsiloxane (MW 7152). This extended wear SHCL enabled an extended release of timolol, dexamethasone, and dexamethasone 21-acetate (hydrophobic and hydrophilic drugs) from 2 weeks to 3 months depending on the composition of the hydrophobic and hydrophilic components. Corneal abscess and opacity were almost healed after wearing a gatifloxacin loaded P(HEMA-co-MAA) hydrogel CL for 48 hours.^{8, 11, 43-45}

Colloidal nanoparticles are submicron-sized particles either encapsulating or mixed with the agent molecules. Two common forms are lipid spheres (liposomes) and colloidal polymeric nanoparticles. Due to their excellent biocompatibility, liposomes are promising candidates for dispersion or surface immobilization on CLs. Nanoparticles are specifically designed to present high affinity for the drug of interest, being either dispersed in the matrix or coating the surface of the CL. Once inserted in the eye the agent diffuses out of the CL matrix away from the nanoparticle towards the tear film. Nanosphere - encapsulated ciprofloxacin incorporated into HEMA-based CL (Acuvue; Johnson & Johnson Vision Care, Inc., Jacksonville, FL) provided a sustained and effective bactericidal activity. Timolol-loaded nanoparticle incorporated in HEMA-based CLs maintained drug stability under refrigerated conditions and the temperature change promoted the drug release upon CL insertion. Nanoparticle loaded gels released timolol in phosphate buffered saline (PBS) for 2-4 weeks within therapeutic levels, looking promising for extended drug release applications. Sustained and effective bactericidal activity was provided by conventional hydrogel CLs incorporating nanosphere-encapsulated ciprofloxacin.^{8, 11, 46-54}

Molecular imprinting consists of creating a template based on a macromolecular memory within a flexible network with a higher affinity towards a drug molecule. Functional monomers thus generated, should favorably interact with a specific drug and this change in formulation improves drug uptake and prolongs delivery. Commonly used monomers for CLs include acrylic acid (AA), acrylamide (AM), methacrylic acid (MAA), methyl methacrylate (MMA) and N-vinyl 2-pyrrolidone (NVP). Increased partitioning due to imprinting depends on the fraction of the functional monomers in CLs, temperature, pressure, drug-functional monomer ratio, initiator concentration and degree of

crosslinking. Imprinted hydrogels composed of HEMA and small amounts of MAA presented higher timolol uptake (12mg timolol/g dry hydrogel) than non-imprinted gels and a drug release during 8–10h. Ketotifen fumarate loading was 6-fold greater in the highest functionalized imprinted hydrogels and their diffusion coefficients were 10 times lower than in less functionalized hydrogels.⁵⁵⁻⁵⁹

Timolol is the most commonly used drug in imprinting studies but hyaluronic acid, diclofenac, ibuprofen, norfloxacin, ketotifen fumarate, acetazolamide, ciprofloxacin and prednisolone have also been studied.^{7,11, 60-62}

Despite being different from typical functional monomers used in molecular imprinting, hyaluronic acid proved to be useful in modifying the drug release curve from model SH lenses having shown a controlled release over 24 hours. As a wetting agent, hyaluronic acid enhances comfort and additionally promotes corneal wound healing and epithelial cell migration.⁶³

Layer-by-layer platforms have been applied for drug delivery due to its simple and mild aqueous manufacturing conditions at room temperature. By sandwiching a poly[lactico-glycolic acid] layer (PLGA) in a 100 micron thick gel extended release of timolol and dexamethasone was achieved from 2 weeks to 3 months. Hydrogel containing a layer of ciprofloxacin loaded PLGA film sandwiched between layers of pHEMA was able to release medication for an extended period and prevent bacterial growth. Chitosan/alginate layers were tested to control the release of different ophthalmic drugs from a silicone-based hydrogel. A double layer of this coating led to a controlled release of diclofenac for one week.⁶⁴⁻⁶⁶

Perspectives and Summary

Research in CL based DCRS shows promising results in a wide variety of situations such as a potential application to treat posterior segment diseases and a platform to culture and transfer limbal cells to treat limbal stem cell deficiency. In vitro experimental results and mathematical modeling suggested that a single CL worn for about 2 hours achieved the same therapeutic effects as hourly instillation of eye drops in controlling corneal cysteine crystals deposition in cystinosis. CL based DCRS can work as a responsive drug delivery platform to environmental triggers such as temperature, pH, ionic interactions or light stimulation. They can assist in the management of corneal persistent epithelial defects by using bandage CLs soaked in vitronectin, a protein that expedites corneal epithelial wound healing and in treating fungal keratitis with CLs as drug reservoir releasing agents for up to 21 days.⁶⁷⁻⁷⁴

Nevertheless, several challenges remain to extend this treatment option to the general population due to CLs' increased risk of infection, to processing, storage, safety, cost-benefit and regulatory issues. To our knowledge, a ketotifen-CL combination (Vistakon/Johnson&Johnson) for patients with allergic conjunctivitis (NCT 00432757) and a plant polysaccharide lubricant alginate acid-CL combination for dry eye CL wearers (NCT 01918410) represent an effort in the clinical application of these systems.^{50, 75-77}

In summary CLs as DCRS are emerging as an effective treatment option for several ocular disorders, including those that can compromise a comfortable and safe CL wear such as glaucoma, allergy and dry eye. By improving bioavailability and effective localized drug delivery these systems can enhance patient compliance, reduce overdosing and avoid unwanted side effects, whilst correcting ametropia. They promote the safe and comfortable wearing of CLs by the incorporation of wetting

agents, provide a timely and efficient medication release in corneal epithelial defect, treat infection and promote healing.

Drug incorporation in CLs can be achieved with several techniques from which soaking is the earliest. There is exciting, ongoing research on techniques to increase drug retention on ocular surface and obtain a sustained release within therapeutic levels. The incorporation of vitamin E, ligands, functional monomers, drug-loaded nanoparticles, molecular imprinting, and layering are under study. An ideal CL drug delivery system should involve high drug loading and controllable drug release without compromising the biomaterial properties of CLs.

ACKNOWLEDGMENTS

The authors wish to thank the Foundation for Science and Technology FCT for funding through the projects UID/QUI/00100/2013, M-ERA.NET/0005/2012 and M-ERA.NET/0007/2012

REFERENCES

- Kopeček J. Hydrogels from soft contact lenses and implants to self-assembled nanomaterials. *J Polym Sci A Polym Chem*. 2009;47(22):5929–46.
- González-Chomón C, Concheiro A, Alvarez-Lorenzo C. Soft contact lenses for controlled ocular delivery: 50 years in the making. *Ther Deliv*. 2013;4(9):1141–61.
- Chauhan A. *Ocular Drug Delivery: Role Of Contact Lenses*. Delhi J Ophthalmol. 2015;26:131-5.
- Hoffman A. Hydrogels for biomedical applications. *Adv Drug Deliv Rev*. 2002; 54(1): 3–12.
- Gooch N, Molokhia SA, Condie R, Burr RM, Archer B, Ambati BK, et al. Ocular drug delivery for glaucoma management. *Pharmaceutics*. 2012; 4(1):197–211.
- Gupta H, Aqil M. Contact lenses in ocular therapeutics. *Drug Discov Today*. 2012;17(9-10):522–7.
- White CJ, Byrne ME. Molecularly imprinted therapeutic contact lenses. *Expert Opin Drug Deliv*. 2010; 7(6):765–80. (
- Guzman-Aranguez A, Colligris B, Pintor J. Contact lenses: promising devices for ocular drug delivery. *J Ocul Pharmacol Ther*. 2013;29(2):189–99.
- Phan CM, Hui A, Subbaraman L, Jones . Insights to using contact lenses for drug delivery. *Clin Exp Pharmacol*. 2014; 3:145.
- Gause S, Hsu KH, Shafor C, Dixon P, Powell KC, Chauhan A. Mechanistic modeling of ophthalmic drug delivery to the anterior chamber by eye drops and contact lenses. *Adv Colloid Interface Sci*. 2015. pii: S0001-8686(15)00142-6. doi: 10.1016/j.cis.2015.08.002.
- Bengani LC, Hsu KH, Gause S, Chauhan A. Contact lenses as a platform for ocular drug delivery. *Expert Opin Drug Deliv*. 2013;10(11):1483-96.
- Morrison PW, Khutoryanskiy VV. (Enhancement in corneal permeability of riboflavin using calcium sequestering compounds. *Int J Pharm*. 2014; 472(1-2): 56–64.
- Jha G, Kumar A. Drug delivery through soft contact lenses: An introduction. *Chron Young Sci*. 2011;2:3-6.
- Morrison P WJ, Khutoryanskiy VV. Advances in ophthalmic drug delivery. *Ther Deliv*. 2014; 5(12):1297–315.
- Hu X , Hao L, Wang H, Yang X, Zhang G, Wang G, Zhang X. Hydrogel contact lens for extended delivery of ophthalmic drugs. *Int J Polymer Sci*. 2011. Article ID 814163. <http://dx.doi.org/10.1155/2011/814163>

16. Kim JY, Kim S, Papp M, Park K, Pinal R. Hydrotropic solubilisation of poorly water-soluble drugs. *J Pharm Sci.* 2010; 99(9): 3953–65.
17. Sanford M. Fluocinolone acetonide intravitreal implant (Iluvien®): in diabetic macular oedema. *Drugs.* 2013;73(2):187-93.
18. Arcinue CA, Cerón OM, Foster CS. A comparison between the fluocinolone acetonide (Retisert) and dexamethasone (Ozurdex) intravitreal implants in uveitis. *J Ocul Pharmacol Ther.* 2013;29(5):501-7.
19. Bethke W. New frontiers in sustained release an update on the most viable strategies for releasing glaucoma drugs over time. *Rev Ophthalmol.* 2015; June. Available from: http://www.reviewofophthalmology.com/content/t/new_technology/c/55174/, last accessed in March, 2016
20. Inokuchi Y, Hironaka K, Fujisawa T et al. Physicochemical properties affecting retinal drug / coumarin-6 delivery from nanocarrier systems via eyedrop administration. *Invest Ophthalmol Vis Sci.* 2010; 51(6): 3162–70.
21. Dixon P, Shafor C, Gause S, Hsu K-H, Powell KC, Chauhan A. Therapeutic contact lenses: a patent review. *Expert Opin Ther Pat.* 2015;25(10):1117–29.
22. Guzman-Aranguiz A, Fonseca B, Carracedo G, Martin-Gil A, Martinez-Aguila A, Pintor J. Dry Eye treatment based on contact lens drug delivery. A review. *Eye Contact Lens.* 2015 Sep 14;1.
23. Hillman JS. Management of acute glaucoma with pilocarpine-soaked hydrophilic lens. *Br J Ophthalmol.* 1974;58(7):674-9.
24. Holland S, Morck D, Schultz C. Treatment of corneal defects with delayed re-epithelization with a medical device/drug delivery system for epidermal growth factor. *Clin Experiment Ophthalmol.* 2012; 40(7):662–8.
25. Jain MR. Drug delivery through soft contact lenses. *Br J Ophthalmol.* 1988; 72(2):150–4.
26. Li CC, Chauhan A. Ocular transport model for ophthalmic delivery of timolol through p-HEMA contact lenses. *J Drug Deliv Sci Tech.* 2007;17(1):69–79.
27. Kim J, Chauhan A. Dexamethasone transport and ocular delivery from poly(hydroxyethyl methacrylate) gels. *Int J Pharm.* 2008; 353(1-2):205-22.
28. Lu C, Mikhail AS, Wang X, Brook MA, Allen C. Hydrogels containing core cross-linked block co-polymer micelles. *J Biomater Sci Polym Ed.* 2012;23(8):1069–90.
29. Karlgard CC, Wong NS, Jones LW, Moresoli C. In vitro uptake and release studies of ocular pharmaceutical agents by silicon containing and p-HEMA hydrogel contact lens materials. *In J Pharm.* 2003; 257(1-2):141-51.
30. Ahmadi F, Oveysi Z, Samani SM, Amoozgar Z. Chitosan based hydrogels: characteristics and pharmaceutical applications *Res Pharm Sci.* 2015;10(1):1–16.
31. Carvalho IM, Marques CS, Oliveira RS, Coelho PB, Costa PC, Ferreira DC. Sustained drug release by contact lenses for glaucoma treatment—a review. *J Control Release.* 2015; 202:76–82.
32. Hsu K-H, Carbia BE, Plummer C, Chauhan A. Dual drug delivery from vitamin E loaded contact lenses for glaucoma therapy. *Eur J Pharm Biopharm.* 2015; 94:312–21.
33. Hsu K-H, de la Jara PL, Ariyavidana A, Watling J, Holden B, Garrett Q, et al. Release of betaine and dexpanthenol from vitamin E modified silicone-hydrogel contact lenses. *Curr Eye Res.* 2015;40(3):267–73.
34. Rad MS, Sajadi Tabassi SA, Moghadam MH, Mohajeri SA. Controlled release of betamethasone from vitamin E-loaded silicone-based soft contact lenses. *Pharm Dev Technol.* 2015 Sep 3;1–6.
35. Paradiso P, Serro AP, Saramago B, Colaço R, Chauhan A. Controlled release of antibiotics from vitamin e-loaded silicone-hydrogel contact lenses. *J Pharm Sci.* 2016;105(3):1164-72.
36. Ribeiro A, Veiga F, Santos D, Torres-Labandeira JJ, Concheiro A, Alvarez-Lorenzo C. Bioinspired imprinted PHEMA-hydrogels for ocular delivery of carbonic anhydrase inhibitor drugs. *Biomacromolecules.* 2011;12(3):701-9.
37. Peng CC, Chauhan A. Extended Cyclosporine delivery by silicone hydrogel contact lenses. *J Control Release.* 2011; 154(3): 267-74
38. Kim J, Peng C-C, Chauhan A. Extended release of dexamethasone from silicone-hydrogel contact lenses containing vitamin E. *J Control Release.* 2010;148(1):110–6.
39. Peng CC, Kim J, Chauhan A. Extended delivery of hydrophilic drugs from silicone-hydrogel contact lenses containing vitamin E diffusion barriers. *Biomaterials.* 2010; 31(14): 4032-47.
40. Sato T, Uchida R, Tanigawa H, Uno K, Murakami A. Application of polymer gels containing side-chain phosphate groups to drug-delivery contact lenses. *J Appl Polymer Sci.* 2005; 98(2): 731–5.
41. Paula AV, Elena FG, Carmen AL, Angel C. Improving the loading and release of NSAIDs from pHEMA hydrogels by copolymerization with functionalized monomers. *J Pharm Sci.* 2007; 96(4):802–13.
42. Morrison PWJ, Cannon CJ, Khutoryanskiy VV. Cyclodextrin-mediated enhancement of riboflavin solubility and corneal permeability. *Mol Pharm.* 2013; 10(2): 756–62. (
43. Shi Y, Lv H, Fu Y, Lu Q, Zhong J, Ma D. Preparation and characterization of a hydrogel carrier to deliver gatifloxacin and its application as a therapeutic contact lens for bacterial keratitis therapy. *Biomed Mater.* 2013;8(5):055007.
44. Brahim S, Narinesingh D, Guiseppi-Elie A. Release characteristics of novel pH sensitive p(HEMA-DMAEMA) hydrogels containing 3-(trimethoxy-silyl) propyl methacrylate. *Biomacromolecules.* 2003;4:1224–31. (
45. Andrade-Vivero P, Fernandez-Gabriel E, Alvarez-Lorenzo C, Concheiro A. Improving the loading and release of NSAIDs from pHEMA hydrogels by copolymerization with functionalized monomers. *J Pharm Sci.* 2007;96(4):802-13.
46. Garhwal R, Shady SF, Ellis EJ, Ellis JY, Leahy CD, McCarthy SP, et al. Sustained ocular delivery of ciprofloxacin using nanospheres and conventional contact lens materials. *Invest Ophthalmol Vis Sci.* 2012 ;53(3):1341-52.
47. Jung HJ, Chauhan A. Temperature sensitive contact lenses for triggered ophthalmic drug delivery. *Biomaterials.* 2012 ;33(7):2289–300.
48. Danion A, Brochu H, Martin Y, Vermette P. Fabrication and characterization of contact lenses bearing surface-immobilized layers of intact liposomes. *J Biomed Mater Res A.* 2007; 82(1): 41-51.
49. Ciolino JB, Hudson SP, Mobbs AN, Hoare TR, Iwata NG, Fink GR. A prototype antifungal contact lens. *Invest Ophthalmol Vis Sci.* 2011; 52(9):6286-91.
50. Gulsen D, Chauhan A. Ophthalmic drug delivery through contact lenses. *Invest Ophthalmol Vis Sci.* 2004; 45(7):2342-7.
51. Gulsen D, Chauhan A. Dispersion of microemulsion drops in HEMA hydrogel: a potential ophthalmic drug delivery vehicle. *Int J Pharm.* 2005; 292(1-2):95–117.
52. Sung AY, Kim TH. Ophthalmic application of poly (HEMA)s containing nanoparticles and dimethylacrylamide. *J Nanosci Nanotechnol.* 2012;12(7):5210-5.(
53. Gupta H, Aqil M, Khar RK, Bhatnagar A, Mittal G. Nanoparticles laden *in situ* gel for sustained ocular drug delivery. *J Pharm Bioallied Sci.* 2013; 5(2):162-5. (
54. Gulsen D, Li CC, Chauhan A. Dispersion of DMPC liposomes in contact lenses for ophthalmic drug delivery. *Curr Eye Res.* 2005;30(12):1071-80.
55. Tieppo A, White CJ, Paine AC, Voyles ML, McBride MK, Byrne ME. Sustained in vivo release from imprinted therapeutic contact lenses. *J Control Release.* 2012; 157(3):391–7.
56. Venkatesh S, Saha J, Pass, S, Byrne ME. Transport and structural analysis of molecular imprinted hydrogels for controlled drug delivery. *Eur J Pharm. Biopharm.* 2008;69(3):852-60.

57. Venkatesh S, Sizemore SP, Byrne ME. Biomimetic hydrogels for enhanced loading and extended release of ocular therapeutics. *Biomaterials*. 2007;28(4):717-24.
58. Ali M, Horikawa S, Venkatesh S, Saha J, Hong JW, Byrne ME. Zero-order therapeutic release from im- printed hydrogel contact lenses within in vitro physiological ocular tear flow. *J Control Release*. 2007;124(3):154-62.
59. Hiratani H, Fujiwara A, Tamiya Y, et al. Ocular release of timolol from molecularly imprinted soft contact lenses. *Biomaterials*. 2005;26(11):1293-8.
60. Hui A, Willcox M, Jones L. In vitro and in vivo evaluation of novel ciprofloxacin-releasing silicone hydrogel contact lenses. *Invest Ophthalmol Vis Sci*. 2014 ;55(8):4896-904.
61. Hiratani H, Fujiwara A, Tamiya Y, Mizutani Y, Alvarez-Lorenzo C. Ocular release of timolol from molecularly imprinted soft contact lenses. *Biomaterials*. 2005; 26(11):1293-8.
62. Hiratani H, Mizutani Y, Alvarez-Lorenzo C. Controlling drug release from imprinted hydrogels by modifying the characteristics of the imprinted cavities. *Macromol Biosci*. 2005;5(8):728-33.
63. Guidi G, Korogiannaki M, Sheardown H. Modification of timolol release from silicone hydrogel model contact lens materials using hyaluronic acid. *Eye Contact Lens*. 2014;40(5):269-76.
64. Bengani LC, Chauhan A. Extended delivery of an anionic drug by contact lens loaded with a cationic surfactant. *Biomaterials*. 2013;34(11):2814-21.
65. Ciolino JB, Hoare TR, Kohane DS. Contact lens drug delivery device. US patent 0329637 A1:2010.
66. Ciolino JB, Hoare TR, Iwata NG, Behlau I, Dohlman CH, Langer R, Kohane DS. A drug-eluting contact lens. *Invest Ophthalmol Vis Sci*. 2009;50(7):3346-52.
67. Brown KD, Low S, Mariappan I, Abberton KM, Short R, Zhang H, et al. Plasma polymer-coated contact lenses for the culture and transfer of corneal epithelial cells in the treatment of limbal stem cell deficiency. *Tissue Eng Part A*. 2014; 20(3-4):646-55.
68. Hsu K-H, Fentzke RC, Chauhan A. Feasibility of corneal drug delivery of cysteamine using vitamin E modified silicone hydrogel contact lenses. *Eur J Pharm Biopharm*. 2013;85(3):531-40.
69. Tavazzi S, Ferraro L, Cozza F, Pastori V, Lecchi M, Farris S, et al. Hydrogen peroxide mechanosynthesis in siloxane-hydrogel contact lenses. *ACS Appl Mater Interfaces*. 2014;6(22):19606-12.
70. Chow S, Di Girolamo N. Vitronectin: a migration and wound healing factor for human corneal epithelial cells. *Invest Ophthalmol Vis Sci*. 2014;55(10):6590-600.
71. Phan C-M, Subbaraman LN, Jones L. In vitro drug release of natamycin from β -cyclodextrin and 2-hydroxypropyl- β -cyclodextrin-functionalized contact lens materials. *J Biomater Sci Polym Ed*. 2014; 25(17):1907-19.
72. Phan C-M, Subbaraman L, Jones L. Contact lenses for antifungal ocular drug delivery: a review. *Expert Opin Drug Deliv*. 2014;11(4):537-46.
73. Phan C-M, Subbaraman L, Liu S, Gu F, Jones L. In vitro uptake and release of natamycin Dex-b-PLA nanoparticles from model contact lens materials. *J Biomater Sci Polym Ed*. 2014; 25(1):18-31.
74. Hsu K-H, Gause S, Chauhan A. Review of ophthalmic drug delivery by contact lenses. *J Drug Deliv Sci Technol*. 2014; 24(2):123-35.
75. Abelson MB, McLaughlin Putting Your Contacts to Work. Attempts to engineer contact lenses that also elute therapeutic drugs face hurdles in both the world of lenses and of drugs. *Rev Ophthalmol*. 2015; May. [cited 2016 Mar 12]. Available from: http://www.reviewofophthalmology.com/content/d/therapeutic_topics/i/3164/c/52895/.
76. Schultz C, Breaux J, Schentag J, Morck D. Drug delivery to the posterior segment of the eye through hydrogel contact lenses. *Clin Exp. Optom*. 2011; 94(75):212-8.
77. Hironaka K, Inokuchi Y, Tozuka Y, Shimazawa M, Hara H, Takeuchi H. Design and evaluation of a liposomal delivery system targeting the posterior segment of the eye. *J Control Release*. 2009; 136(3):247-53.

Corresponding Author:

Helena Prior Filipe
 Departament of Ophthalmology, Hospital of the Armed Forces -
 Lisbon, Azinhaga dos Ulmeiros, Paço do Lumiar, 1690-020
 Lisbon, Portugal - Department of Ophthalmology, Hospital of
 SAMS, Rua Fialho de Almeida, 1070-128 - Lisbon, Portugal
 Phone: +351967061457
 E-mail: hpriorfilipe@gmail.com